

**PRODUCT
DESCRIPTION**

- A high solids two pack epoxy phenolic tank lining.
- Excellent chemical resistance to a wide range of chemicals.
 - Complies with the requirements of Lloyds Register of Shipping rules.

DESIGNED USE

- As an internal tank lining for chemical storage tanks.
- Suitable as a topcoat for upto C5 Environment as per ISO12944 Part 2

PHYSICAL DATA

VOLUME SOLIDS (Based on ASTM D2697)	82 % \pm 2 %
TYPICAL DRY FILM THICKNESS	125 microns
WET FILM THICKNESS	152 microns
THEORETICAL COVERAGE	6.56 m ² /litre @ 125 microns DFT
VOC "As Supplied" (Based on ASTM D3960)	180 gms/ltr
COLOUR	Buff & Grey
FINISH	Semi-Gloss

**APPLICATION
DETAILS****METHOD OF APPLICATION :****AIRLESS SPRAY**

This is the recommended method of application:
Maximum 5% Thinner may be added.
Tip Size: 0.48 - 0.68 mm (0.019 - 0.027 in)
Pressure: 110 - 160 kg/cm² (1600 – 2300 psi)

BRUSH OR ROLLER

May be used for difficult shapes or touch-up.
However, additional coats may be required to achieve the recommended film thickness.

DRYING TIME:

Surface Temperature	Touch Dry	Hard Dry	Re coating Interval		Pot Life
			Minimum	Maximum	
15°C	16 Hrs	32 Hrs	24 Hrs	10 Days	2 Hrs
25°C	8 Hrs	16 Hrs	16 Hrs	7 Days	1 Hr
35°C	4 Hrs	8 Hrs	8 Hrs	5 Days	½ Hr
45°C	2 Hrs	6 Hrs	6 Hrs	3 Days	< ½ Hr

NO. OF COMPONENTS Two

Mixing Ratio As per Pack Size

Application Conditions Do not apply this product if the Relative Humidity exceeds 85% or if the substrate temperature is within 3°C of the dew point

**ADDITIONAL
INFORMATION**

Thinner / Cleaning solvent	Solvalux 7-45
Storage Instruction	Store in a cool shaded dry area
Flash Point	Mixed 20°C
Packaging	5 litres & 20 litres
Shelf Life	12 months from the date of manufacture.

**SURFACE
PREPARATION**

This product should be applied to a surface that has been blast cleaned and suitably primed (e.g. with EPILUX Primers).

- Remove all wax, oil and grease by solvent cleaning in accordance with the guide lines given by SSPC-SPI.
- Where necessary remove weld spatter and round off all rough weld seams and sharp edges to a smooth surface.
- Abrasive blast clean to a minimum standard of Sa 2½ Swedish Standard SIS 05 59 00 or ISO 8501-1 : 1988
- Any surface defects revealed by blast cleaning should be ground, filled or treated in a suitable manner.
- An average surface profile of 50 microns is acceptable, but this average should not exceed 75 microns.
- After blasting, remove dust from the surface.
- The surface to be coated must also be clean and dry.

**PRODUCT USE
RESTRICTIONS**

- Do not vary the recommended film thickness without prior consultation.
- This product will not cure below 10°C.
- A moisture and oil trap in the main air line is essential for the successful application of this product.
- As common with all Epoxy products, this product also will tend to discolour and chalk on exposure to direct sunlight.
- May also be applied between 125 and 150 microns DFT.
- Contact Berger Representative for suggesting suitable paint system

**SAFETY
PRECAUTIONS**

- Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust masks and gloves. Use a barrier cream.
- Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapor or spray.
- This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge. In case of fire – blanket flames with foam, carbon dioxide or dry chemicals
- Refer to MSDS for further information.

FIRST AID

- Eyes: In the event of accidental splashes, flush eyes with water immediately and obtain medical advice
- Skin: Wash skin thoroughly with soap and water or approved industrial cleaner.
- DO NOT USE solvent or thinners.
- Inhalation: Remove to fresh air, loosen collar and keep patient rested.
- Ingestion: In case of accidental ingestion, DO NOT INDUCE VOMITING.
Obtain immediate medical attention

DISCLAIMER

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.